

# **Ultramid® B3ZG7 SC** **Polyamide 6**



## **Product Description**

Ultramid B3ZG7 SC is an uncolored, 35% glass reinforced, heat stabilized, impact modified PA6 injection molding grade.

PHYSICAL	ISO Test Method	Property Value	
Density, g/cm <sup>3</sup>	1183	1.37	
Moisture, %	62		
(50% RH)		1.8	
(Saturation)		6.0	
RHEOLOGICAL	ISO Test Method	Dry	Conditioned
Melt Flow Rate (235 C/5 Kg), g/10min.	1133	2.3	-
MECHANICAL	ISO Test Method	Dry	Conditioned
Tensile Modulus, MPa	527		
23C		10,200	-
Tensile stress at break, MPa	527		
23C		169	-
Tensile strain at break, %	527		
23C		4.1	-
Flexural Modulus, MPa	178		
23C		9,300	-
IMPACT	ISO Test Method	Dry	Conditioned
Izod Notched Impact, kJ/m <sup>2</sup>	180		
-40C		18	-
23C		24	-
Charpy Notched, kJ/m <sup>2</sup>	179		
-40C		17	-
-30C		17	-
23C		22	-
Charpy Unnotched, kJ/m <sup>2</sup>	179		
-30C		113	-
23C		102	-
THERMAL	ISO Test Method	Dry	Conditioned
Melting Point, C	3146	219	-
HDT A, C	75	206	-
HDT B, C	75	219	-

## **Processing Guidelines**

### **Material Handling**

Max. Water content: 0.08%

Product is supplied in sealed containers and drying prior to molding is not required. If drying becomes necessary, a dehumidifying or desiccant dryer operating at 80C (176F) is recommended.

Drying time is dependent on moisture level however 2-4 hours is generally sufficient. Further information concerning safe handling procedures can be obtained from the Safety Data Sheet.

Alternatively, please contact your BASF representative.

## Typical Profile

Melt Temperature 270-295C (518-563F)  
Mold Temperature 80-95C (176-203F)  
Injection and Packing Pressure 35-125 bar (500-1800psi)  
Rear Zone 245-275C (473-527F)  
Center Zone 260-285C (500-545C)  
Front Zone 270-295C (518-563F)  
Nozzle 270-295C (518-563F)

## Mold Temperatures

This product can be processed over a wide range of mold temperatures; however, for applications where aesthetics are critical, a mold surface temperature of 80-95C (176-203F) is required.

## Pressures

Injection pressure controls the filling of the part and should be applied for 90% of ram travel. Packing pressure affects the final part and can be used effectively in controlling sink marks and shrinkage. It should be applied and maintained until the gate area is completely frozen off.

Back pressure can be utilized to provide uniform melt consistency and reduce trapped air and gas. Minimal back pressure should be utilized to prevent glass breakage.

## Fill Rate

Fast fill rates are recommended to ensure uniform melt delivery to the cavity and prevent premature freezing. Surface appearance is directly affected by injection rate.

## Note

Although all statements and information in this publication are believed to be accurate and reliable, they are presented gratis and for guidance only, and risks and liability for results obtained by use of the products or application of the suggestions described are assumed by the user. NO WARRANTIES OF ANY KIND, EITHER EXPRESS OR IMPLIED, INCLUDING WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE, ARE MADE REGARDING PRODUCTS DESCRIBED OR DESIGNS, DATA OR INFORMATION SET FORTH. Statements or suggestions concerning possible use of the products are made without representation or warranty that any such use is free of patent infringement and are not recommendations to infringe any patent. The user should not assume that toxicity data and safety measures are indicated or that other measures may not be required.