

# Ultradur® B 4300 G4 High Speed Unc.

## Polybutylene Terephthalate (PBT)



### Product Description

Ultradur B 4300 G4 High Speed Unc. is a high flow, fast cycling with low warpage, 20% glass filled, injection molding PBT for industrial parts, rigid tough and dimensional stable applications.

### Applications

Typical applications include windshield wiper arms, printed circuit boards, housing, consoles, contact carriers, covers.

PHYSICAL	ISO Test Method	Property Value
Density, g/cm <sup>3</sup>	1183	1.45
RHEOLOGICAL	ISO Test Method	Property Value
Melt Volume Rate (250 C/2.16 Kg), cc/10min.	1133	21
MECHANICAL	ISO Test Method	Property Value
Tensile Modulus, MPa	527	
23C		7,110
Tensile stress at break, MPa	527	
23C		122
Tensile strain at break, %	527	
23C		3.2
IMPACT	ISO Test Method	Property Value
Charpy Notched, kJ/m <sup>2</sup>	179	
23C		7.4
Charpy Unnotched, kJ/m <sup>2</sup>	179	
-30C		43
23C		51
THERMAL	ISO Test Method	Property Value
Melting Point, C	3146	223
HDT A, C	75	195
HDT B, C	75	220

### Processing Guidelines

#### Material Handling

Max. Water content: 0.04%

To ensure optimum part performance, this product must be dried prior to molding and maintained at a moisture level of less than 0.04%. Dehumidifying or desiccant dryers operating at 100-120C (212-248F) for 4 hours drying time are recommended. Further information concerning safe handling procedures can be obtained from the Safety Data Sheet. Alternatively, please contact your BASF representative.

#### Typical Profile

Melt Temperature 250-270C (482-518F)

Mold Temperature 60-100C (140-212F)

Injection and Packing Pressure 35-125 bar (500-1500 psi)

#### Mold Temperatures

This product can be processed over mold temperatures of 60-100C (140-212F); however, for optimizing surface appearance, dimensional stability and part performance, mold surface temperatures of at least 80C (176F) are preferred.

## **Pressures**

Injection pressure controls the filling of the part and should be applied for 90% of ram travel. Packing pressure affects the final part and can be used effectively in controlling sink marks and shrinkage. It should be applied and maintained until the gate area is completely frozen off.

Back pressure can be utilized to provide uniform melt consistency and reduce trapped air and gas. A maximum of 10 bar (145 psi) is recommended due to the risk of excessive shear.

## **Fill Rate**

Fast fill rates are recommended to ensure uniform melt delivery to the cavity and prevent premature freezing. Surface appearance is directly affected by injection rate.

## **Note**

Although all statements and information in this publication are believed to be accurate and reliable, they are presented gratis and for guidance only, and risks and liability for results obtained by use of the products or application of the suggestions described are assumed by the user. NO WARRANTIES OF ANY KIND, EITHER EXPRESS OR IMPLIED, INCLUDING WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE, ARE MADE REGARDING PRODUCTS DESCRIBED OR DESIGNS, DATA OR INFORMATION SET FORTH. Statements or suggestions concerning possible use of the products are made without representation or warranty that any such use is free of patent infringement and are not recommendations to infringe any patent. The user should not assume that toxicity data and safety measures are indicated or that other measures may not be required.